

AMENDMENTS TO THE SPECIFICATION

Please amend the specification as follows:

Amend paragraph [0013] on page 5 of the specification to read as follows:

Said minute concavity and convexity on the surface of adhesive layer can be provided either by pressing said adhesive layer with a press having minute saliences, or formed by spray-coating granular adhesive on the surface of core material. Or said minute concavity and convexity on the surface of adhesive layer may be formed by blast processing. In case of blast processing, if finely ~~erashed~~ crushed dry ice or ice is used, then since the blast material melts after finishing the concavity and convex process on the adhesive layer, said blast material does not remain on the adhesive layer.